

# Test Report



Report No. A2190226179101001R1

Page 1 of 5

Applicant Tesa Plant (Suzhou) Co.,Ltd

Address No. 451 Zhong Nan Street, Sip, Suzhou, China

**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client**

Sample Name tesa 58375  
Type 130um  
Sample Receiving State Normal  
Sample Received Date Aug. 29, 2019  
Testing Period Aug. 29, 2019-Sep. 4, 2019

**Test Requested**

No.	Test Item
1	Flammability(Thin material vertical burning)

**Test Result(s):**Please see the following pages.

Approved by Star Shi

Date Sep. 4, 2019

Star Shi  
Approved Signatory  
Centre Testing International Corporation  
Hangzhou) Co., Ltd

No.R8B7B748CF  
Room 105,Building 1,No.600,N0.21 Street, Baiyang Road, Hangzhou  
Economic & Technological Development Zone Hangzhou, China;



# Test Report


Report No. A2190226179101001R1

Page 2 of 5

## Tested Sample(s)

Sample No.	Sample Name
A2190226179101001	tesa 58375

## Sample Photo(s)



A2190226179101001

# Test Report

Report No. A2190226179101001R1

Page 3 of 5

**Test Item: Flammability(Thin material vertical burning)**

## 1. Test Equipment

Equipment Name	Model
Horizontal and vertical burning tester	UL94-X

## 2. Environmental Conditions

Temperature: 22.6°C ; Humidity: 54%RH

## 3. Test Standard: UL 94-2018

## 4. Test Result(s)

**Sample sizes** 200mm×50mm×0.13mm

### Condition

Condition 1 in environment of (23±2)°C and humidity of (50±10)%RH for 48h.

Condition 2 in a 70°C oven for 168h, then a calcium chloride desiccators for at least 4h to cool to room temperature.

Note: This specimens were only placed in condition 1

### Test Criteria

Criteria conditions	VTM-0	VTM-1	VTM-2
Afterflame time for each individual specimen $t_1$ or $t_2$	≤10s	≤30s	≤30s
Total afterflame time for any condition set ( $t_1$ plus $t_2$ for the 5 specimens)	≤50s	≤250s	≤250s
Afterflame plus afterglow time for each individual specimen after the second flame application ( $t_2+t_3$ )	≤30s	≤60s	≤60s
Did the afterflame or afterglow of any specimen progress up to the 125mm mark	No	No	No
Was the cotton indicator ignited by flaming particles or drops	No	No	Yes

# Test Report

Report No. A2190226179101001R1

Page 4 of 5

## Results

Sample No.	Condition 1				
	1st	2nd	3rd	4th	5th
Afterflame time $t_1$ , s	0	1	0	0	0
Afterflame time $t_2$ , s	1	0	1	2	1
Afterglow time $t_3$ , s	0	0	0	0	0
Total afterflame time, s	6				
$t_2+t_3$ , s	1	0	1	2	1
Did the afterflame or afterglow of any specimen progress up to the 125mm mark	No	No	No	No	No
Flaming particles or drops	No	No	No	No	No
Was the cotton indicator ignited by flaming particles or drops	No	No	No	No	No

## Evaluation

The submitted sample to be preconditioned at  $(23 \pm 2)^\circ\text{C}$  and  $(50 \pm 10)$  percent relative humidity for a minimum of 48 hours **meet** the requirement prescribed in VTM-0 combustion test.

**Statement:** The test results relate only to the behaviour of the test specimens under the conditions of this test and that these results shall not be used to infer the fire hazards of the materials in other forms or under other fire conditions.

# Test Report

Report No. A2190226179101001R1

Page 5 of 5

## Sample Photo(s) after the test



### Remark:

1. The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.
2. This testing report revised "Sample Name" and deleted "Lot No." based on the original report of No.A2190226179101001. This testing report displaces the original one which was invalid since the date of this testing report released.

\*\*\* End of Report \*\*\*

### Statement:

- 1.This report is considered invalid without approved signature, special seal and the seal on the perforation;
- 2.The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;
- 3.The result(s) shown in this report refer(s) only to the sample(s) tested;
- 4.Without written approval of CTI, this report can't be reproduced except in full;
- 5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.