



# tesa<sup>®</sup> 88642

## Product Information



### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing	non-woven	• Color	translucent
• Type of adhesive	tackified acrylic	• Color of liner	white/blue logo
• Type of liner	PE-coated paper	• Thickness of liner	130 µm
• Total thickness	120 µm		

### Properties/Performance Values

• Static shear resistance at 70°C	very good	• Temperature resistance long term	70 °C
• Tack	good	• Temperature resistance short term	160 °C

### Adhesion to Values

• ABS (initial)	8.5 N/cm	• PE (after 3 days)	5 N/cm
• ABS (after 3 days)	10.2 N/cm	• PET (initial)	6.7 N/cm
• Glass (initial)	7.5 N/cm	• PP (initial)	5.8 N/cm
• Glass (after 3 days)	9.5 N/cm	• PP (after 3 days)	7 N/cm
• PC (initial)	9.1 N/cm	• PVC (initial)	6.5 N/cm
• PC (after 3 days)	11.7 N/cm	• Steel (initial)	7.5 N/cm
• PE (initial)	4.4 N/cm	• Steel (after 3 days)	10.1 N/cm

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88642>