

tesa® 6190

**Product Information** 



9.5 N/cm 6.8 N/cm 7.9 N/cm 10.6 N/cm 12 N/cm 13 N/cm 11.5 N/cm 11.8 N/cm

# Sustainable Aspects

Ì

#### For more information: https://www.tesa.com/product-sustainability

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li></ul>	PET film tackified acrylic	<ul><li>Color</li><li>Color of liner</li></ul>	transparent red				
Type of liner	MOPP	Thickness of liner	80 µm				
Total thickness	205 µm	Weight of liner	72 g/m <sup>2</sup>				
Properties/Performance Values							
<ul> <li>Elongation at break</li> </ul>	30 %	<ul> <li>Static shear resistance at 23°C</li> </ul>	very good				
<ul> <li>Tensile strength</li> </ul>	130 N/cm	<ul> <li>Static shear resistance at 40°C</li> </ul>	very good				

<ul> <li>lensile strength</li> </ul>	130 N/cm	<ul> <li>Static shear resistance at 40°C very good</li> </ul>
<ul> <li>Ageing resistance (UV)</li> </ul>	good	• Tack good
Chemical Resistance	good	<ul> <li>Temperature resistance long 100 °C</li> </ul>
Humidity resistance	very good	term
Softener resistance	good	Temperature resistance min40 °C
		Temperature resistance short 200 °C
		term

## **Adhesion to Values**

• ABS (initial)	10.3 N/cm	<ul> <li>PET (after 14 days)</li> </ul>
<ul> <li>ABS (after 14 days)</li> </ul>	12 N/cm	• PP (initial)
<ul> <li>Aluminium (initial)</li> </ul>	9.2 N/cm	<ul> <li>PP (after 14 days)</li> </ul>
<ul> <li>Aluminium (after 14 days)</li> </ul>	10.6 N/cm	• PS (initial)
PC (initial)	12.6 N/cm	<ul> <li>PS (after 14 days)</li> </ul>
<ul> <li>PC (after 14 days)</li> </ul>	14 N/cm	PVC (initial)
• PE (initial)	5.8 N/cm	<ul> <li>PVC (after 14 days)</li> </ul>
• PE (after 14 days)	6.9 N/cm	Steel (initial)
<ul> <li>PET (initial)</li> </ul>	9.2 N/cm	<ul> <li>Steel (after 14 days)</li> </ul>





**Product Information** 

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 10/11/24 – en-AU