



tesa[®] 4309 PV1



Product Information

Car masking tape for paint spraying up to 120°C

Product Description

tesa[®] 4309 is a finely crêped, extremely stretchable and flexible paper masking tape for spray painting with subsequent oven-drying up to a temperature of 120 °C.

Sustainable Aspects

53% bio-based content in total product excluding liner (by weight)



For more information: <https://www.tesa.com/product-sustainability>

Product Features

- The excellent adhesion of fillers or paints (water- or solvent-borne) to the reverse side of the tape prevents any kind of paint flaking.
- After the oven drying process with temperatures up to 120° C, tesa[®] 4309 can be easily removed without tearing and without leaving any residues.
- The flexible masking tape is resistant to wet sanding and features excellent adhesion to various surfaces

Application Fields

- Lacquering work
- Can be used on painted metal, rubber, glass and chromed parts
- Excellent flexibility for curves

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------------------|--|--------|
| • Backing material | slightly-creped paper | • Bio-based content of liner by weight (acc. EN 16785) | 53 % |
| • Type of adhesive | natural rubber | • Total thickness | 170 µm |

Properties/Performance Values

- | | | | |
|-----------------------|---------|-----------------------------------|-----------|
| • Elongation at break | 12 % | • Hand tearability | very good |
| • Tensile strength | 47 N/cm | • Temperature resistance (30 min) | 120 °C |
| • Easy to remove | yes | | |

For latest information on this product please visit <http://l.tesa.com/?ip=04309>



tesa[®] 4309 PV1

Product Information

Adhesion to Values

- steel 3.5 N/cm

Additional Information

The product is resistant to wet sanding and the very good adhesion of fillers or paints (water or solvent-based) to the reverse side of the tape prevents any kind of flaking.

After the oven drying process with temperatures up to 120 °C tesa[®] 4309 can be easily removed without tearing and without leaving any residues.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04309>