



tesa[®] 62935

Product Information



1000µm double-sided PE foam tape

Product Description

tesa[®] 62935 is a double-sided PE foam tape for constructive mounting applications. It consists of a high quality PE foam offering a high internal strength and is equipped with a tackified acrylic adhesive.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorption

Application Fields

Example mounting applications include but are not limited to:

- Mirrors and coloured glass panels
- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded plastic parts

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing material | PE foam | • Total thickness | 1000 µm |
| • Type of adhesive | tackified acrylic | • Colour | black/white |



tesa® 62935

Product Information

Properties/Performance Values

• Elongation at break	345 %	• Static shear resistance at 23°C	good, medium
• Tensile strength	12 N/cm	• Static shear resistance at 40°C	good, medium
• Ageing resistance (UV)	good	• Tack	good, medium
• Humidity resistance	very good	• Temperature resistance long term duration	80 °C
• Softener resistance	medium	• Temperature resistance short term duration	80 °C

Adhesion to Values

• Aluminium (initial)	17 N/cm	• PP (initial)	2.8 N/cm
• Aluminium (after 14 days)	17 N/cm	• PP (after 14 days)	6 N/cm
• PE (initial)	2.7 N/cm	• PVC (initial)	8 N/cm
• PE (after 14 days)	3 N/cm	• PVC (after 14 days)	17 N/cm
• PET (initial)	12.5 N/cm	• Steel (initial)	17 N/cm
• PET (after 14 days)	17 N/cm	• Steel (after 14 days)	17 N/cm

Additional Information

Liner variants:

- PV0 brown glassine paper (71 µm)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62935>