



# tesa<sup>®</sup> 51865 - Team 4965 Differential



## Product Information

165µm double sided transparent asymmetrical filmic tape

## Product Description

tesa<sup>®</sup> 51865 is an asymmetrical transparent double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

The covered side of tesa<sup>®</sup> 51865 has a high coating weight for maximum flexibility and versatility on multiple surface demands. The open side of tesa<sup>®</sup> 51865 shows a reduced coating weight that guarantees a secure bond to flat profiles laminated under controlled conditions.

tesa<sup>®</sup> 51865 features especially:

- Excellent bond to extruded trims and profiles
- Reliable bond even to LSE ( Low Surface Energy) substrates
- Immediate usability right after assembly
- Suitability for most demanding applications such as heavy stress, high temperatures or critical substrates

## Product Features

- Asymmetrical product design with 100 µm adhesive on liner-covered side, 60 µm on open side
- Excellent bond to extruded trims and profiles
- Skin contact certification according to ISO 10993-5 and ISO 10993-10
- Reliable bond even on low surface energy surfaces
- Immediate usability right after assembly
- Low VOC – measured according to VDA 278 analysis

## Application Fields

- Mounting of decorative trims and profiles in the furniture industry
- Lamination of magnetic stripes
- Roller blind production
- Equipping extruded plastic profiles with transparent double sided filmic tape

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                   |                   |             |
|--------------------|-------------------|-------------------|-------------|
| • Backing material | PET film          | • Total thickness | 165 µm      |
| • Type of adhesive | tackified acrylic | • Colour          | transparent |

For latest information on this product please visit <http://l.tesa.com/?ip=51865>



# tesa<sup>®</sup> 51865

## - Team 4965 Differential

### Product Information

#### Properties/Performance Values

• Elongation at break	55 %	• Static shear resistance at 23°C	good, medium
• Tensile strength	20 N/cm	• Static shear resistance at 40°C	good, medium
• Ageing resistance (UV)	very good	• Tack	good, medium
• Chemical resistance	good	• Temperature resistance long term duration	100 °C
• Humidity resistance	very good	• Temperature resistance min.	-40 °C
• Softener resistance	good, medium	• Temperature resistance short term duration	200 °C

#### Adhesion to Values

• ABS (initial)	9.5 N/cm	• PET (covered side, after 14 days)	10.5 N/cm
• ABS (after 14 days)	10 N/cm	• PET (covered side, initial)	10 N/cm
• ABS (covered side, after 14 days)	13 N/cm	• PP (initial)	7 N/cm
• ABS (covered side, initial)	12 N/cm	• PP (after 14 days)	8 N/cm
• Aluminium (initial)	9 N/cm	• PP (covered side, after 14 days)	8.5 N/cm
• Aluminium (after 14 days)	9.5 N/cm	• PP (covered side, initial)	8 N/cm
• Alu (covered side, after 14 days)	12.5 N/cm	• PS (initial)	9 N/cm
• Aluminium (covered side, initial)	12 N/cm	• PS (after 14 days)	11 N/cm
• PC (initial)	9 N/cm	• PS (covered side, after 14 days)	13.5 N/cm
• PC (after 14 days)	12 N/cm	• PS (covered side, initial)	12 N/cm
• PC (covered side, after 14 days)	15 N/cm	• PVC (initial)	7 N/cm
• PC (covered side, initial)	13 N/cm	• PVC (after 14 days)	11 N/cm
• PE (initial)	6.5 N/cm	• PVC (covered side, after 14 days)	14 N/cm
• PE (after 14 days)	7 N/cm	• PVC (covered side, initial)	9 N/cm
• PE (covered side, after 14 days)	8 N/cm	• Steel (initial)	9.6 N/cm
• PE (covered side, initial)	7 N/cm	• Steel (after 14 days)	11.5 N/cm
• PET (initial)	9 N/cm	• Steel (covered side, after 14 days)	14.5 N/cm
• PET (after 14 days)	9.5 N/cm	• Steel (covered side, initial)	13.3 N/cm

#### Additional Information

Liner variants:

PV0: brown glassine paper (71µm; 82g/m<sup>2</sup>)

PV6: red MOPP-film (80µm; 72g/m<sup>2</sup>)



# tesa<sup>®</sup> 51865 - Team 4965 Differential

Product Information

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=51865>