



tesa® 6190 Combitape



Product Information

Double-sided filmic box sealing tape with integrated tear-tape

Product Description

tesa® Combitape is a transparent double-sided tape consisting of a PET-film backing and a tackified acrylic adhesive. tesa® Combitape is supplied with fingerlift (extended liner) and integrated tear-tape.

tesa® Combitape has been designed for corrugated board cartons and features:

- Fast liner removal due to fingerlift
- High initial adhesion for fast closure
- Reliable bonding performance even at high temperature
- Implement closure and opening function in limited space

Sustainable Aspects

- tesa® 6190 Combitape Next Gen with -39% CO₂ emissions* compared to tesa® 6190 Combitape
- Biomass balanced tackified acrylic adhesive
- 90% PCR PET in the backing



For more information: <https://www.tesa.com/product-sustainability>

Product Features

- Implementing closure and opening function in limited space
- Fast liner removal due to fingerlift
- High initial adhesion for fast closure
- Reliable bonding performance even at high temperatures and on rough corrugated-board surfaces
- Recycling friendly according to the INGEDE method

Application Fields

- Self-adhesive mail order boxes
- CD and book cartons

For latest information on this product please visit <http://l.tesa.com/?ip=06190>



tesa® 6190 Combitape

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	PET film	• Colour	transparent
• Type of adhesive	tackified acrylic	• Colour of liner	red
• Type of liner	MOPP	• Thickness of liner	80 µm
• Total thickness	205 µm	• Weight of liner	72 g/m ²

Properties/Performance Values

• Elongation at break	30 %	• Static shear resistance at 23°C	very good
• Tensile strength	130 N/cm	• Static shear resistance at 40°C	very good
• Ageing resistance (UV)	good	• Tack	good
• Chemical resistance	good	• Temperature resistance long term duration	100 °C
• Humidity resistance	very good	• Temperature resistance min. term duration	-40 °C
• Softener resistance	good	• Temperature resistance short term duration	200 °C

Adhesion to Values

• ABS (initial)	10.3 N/cm	• PET (after 14 days)	9.5 N/cm
• ABS (after 14 days)	12 N/cm	• PP (initial)	6.8 N/cm
• Aluminium (initial)	9.2 N/cm	• PP (after 14 days)	7.9 N/cm
• Aluminium (after 14 days)	10.6 N/cm	• PS (initial)	10.6 N/cm
• PC (initial)	12.6 N/cm	• PS (after 14 days)	12 N/cm
• PC (after 14 days)	14 N/cm	• PVC (initial)	8.7 N/cm
• PE (initial)	5.8 N/cm	• PVC (after 14 days)	13 N/cm
• PE (after 14 days)	6.9 N/cm	• Steel (initial)	11.5 N/cm
• PET (initial)	9.2 N/cm	• Steel (after 14 days)	11.8 N/cm

Additional Information

*Product Carbon Footprint (PCF) reduction for the new tesa® 6190 Combitape Next Gen (2000m x 23mm spool, PV0 red MOPP liner) compared to the current tesa® 6190 Combitape (2000m x 23mm spool, PV0 red MOPP liner) calculated in 2024 with Cradle-to-Gate values, including biogenic carbon uptake. The calculation of the CO₂ footprint was conducted in 2024, following the same approach as the ISO 14067-compliant comparative PCF study for tesa® 4965 Original Next Gen, available on tesa.com/4965-report. For detailed information on the tesa® 6190 Combitape Next Gen Product Carbon Footprint, please contact your local tesa sales representative.



tesa[®] 6190 Combitape

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=06190>