

tesa® 6957 PV1 Black Glossy FPA



Product Information

9657

Product Description

tesa[®] 6957 is a high heat resistant two-layer, brittle acrylic laser markable film with a unique, forgery-proof watermark design that is embedded into the material as prove of originality.

Marking and cutting are achieved by laser in one step, which makes it possible to realize any desirable label variation and format using only one material. The product is highly durable and resistant against thermal, chemical, mechanical and environmental (weathering) influences for secure traceability over entire vehicle lifetime.

The adhesive system consists of a special acrylic adhesive system, which leaves an UV-detectable trace ("UV-Footprint") on most surfaces as required by GB/T 25978 (P.R.C.) and NHTSA §541.5 (USA).

Application Fields

Depending on the type of application, our laser markable films are available in different grades, either for standard warning and instruction content or for demanding theft relevant vehicle identification and certification labels and anti-theft part marking.

tesa[®] 6957 is specially designed to also fulfill the requirements of GB/T 25978 (P.R.C.) for F-Type labels (engine and transmission).

This high-performance product is used as a tamper evident vehicle identification and certification label as well as anti-theft parts marking for secure traceability over the entire vehicle lifetime.

Computer Aided Manufacturing: Labels are designed and produced on site, guaranteeing highest flexibility and quick adaptation of format and contents, e.g. car model relevant data, different languages, sequential serial numbers.



tesa® 6957 PV1 Black Glossy FPA

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

Backing materialType of adhesiveType of liner	Acrylic acrylic coated paper	Total thicknessAdhesive weightThickness of tape	122 μm 25 g/m² 95 μm
Product Assortment			
Available ColoursAvailable formats	black, black matt 100mm, 120mm, PV3: 300m, PV1: 200m	Available thicknesses	PV3: 95μm, PV1: 127μm
Properties/Performance Values			
 Ageing resistance (UV) Chemical resistance Frost resistance Humidity resistance Shelf life time 	very good very good -40 °C very good 12 months	 Suitable laser Tamper evidence Temperature resistance long term duration Temperature resistance short term duration 	CO ₂ , Nd:YAG, Yb:YAG yes 150 °C 250 °C

Adhesion to Values

steel

1.8 N/cm

Storage Conditions

Storage Conditions

- Original packaging excluding exposure of laser markable film to light and heating source
- Storage of rolls in a horizontal position
- Ideal storage at standard room temperature and rel. humidity according ISO 554
- Refrigerated tapes need to be reconditioned prior to their use. An application below 10°C has to be avoided as this may not provide sufficient immediate adhesion.
- After opening the packaging, the tape shall be used as soon as possible

Additional Information

tesa[®] 6957 series is available in different product variants to fulfill our customers' requirements for different applications and substrates.

- + 6957 PV3 black/ white glossy: Adhesive $25g/m^2$, Thickness $95\mu m$ without Liner. Color code: 04
- 6957 PV3 black/ white matt: Adhesive $25g/m^2$, Thickness $95\mu m$ without Liner. Color code: 28

For latest information on this product please visit http://l.tesa.com/?ip=06957



tesa® 6957 PV1 Black Glossy FPA

Product Information

Additional Information

- + 6957 PV1 black/ white glossy: Adhesive $35g/m^2$, Thickness $127\mu m$ without Liner. Color code: 04
- + 6957 PV1 black/ white matt: Adhesive 35g/m², Thickness 127 μ m without Liner. Color code: 28

Optional: LSE adhesive with UV-Footprint (MU56): A special acrylic adhesive system with high bonding power improved for difficult surfaces such as LSE plastics, powder coatings and textured/structured surfaces. It leaves an UV-detectable trace ("UV-Footprint") on most surfaces as required by GB 25978 (P.R.C.) and NHTSA §541.5 (USA). This special variant is available upon request.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 3 of 3 – as of 14/08/24 – en-GB