




tesa[®] 58362

Product Information



tesa[®] 58362 is a 100µm double-sided transparent PET filmic tape

Product Description

The tackified acrylic adhesive gives this product a good peel strength and very high dynamic shear between two polar substrates. The 50µm transparent PET filmic backing offers excellent electrical insulation property. The glassine liner ensures it can be easily released without adhesive residue. It can meet the strict automotive environmental and long-term durability requirement.

Product Features

- High dynamic shear (>2MPa) between cells in EV battery.
- Outstanding reliability according to automotive industry requirement.
- Product assortment available from 50µm to 200µm.

Application Fields

- Demanding mounting applications in ePowertrain.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-----------------|
| • Backing material | PET | • Total thickness | 100 µm |
| • Type of adhesive | tackified acrylic | • Colour | transparent |
| • Type of liner | glassine | • Colour of liner | brown/blue logo |

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|---|------------|
| • Dielectric breakdown voltage | 9800 V | • Temperature range | -40~125 °C |
| • Static shear resistance at 23°C | very good | • Temperature resistance | very good |
| • Static shear resistance at 40°C | very good | • Temperature resistance long term duration | 125 °C |
| • Static shear resistance at 70°C | very good | | |

Adhesion to Values

- | | | | |
|-----------------------|----------|-------------------------|----------|
| • Aluminium (initial) | 5.7 N/cm | • Steel (initial) | 7 N/cm |
| • PC (initial) | 6.7 N/cm | • Steel (after 14 days) | 8.5 N/cm |



tesa[®] 58362

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58362>