




tesa[®] 58363

Product Information



150 µm double-sided transparent PET filmic tape

Product Description

The tackified acrylic adhesive gives this product a good peel strength and very high dynamic shear (>2MPa) between two polar substrates. The 100µm transparent PET filmic backing offers excellent electrical insulation property. The glassine liner ensures it can be easily released without adhesive residue. It can meet the strict automotive environmental and long-term durability requirement.

Product Features

- Excellent electrical insulation property
- Friendly to converting process
- Reliable peel adhesion on polar substrates
- High dynamic shear performance between polar substrate (>2MPa)

Application Fields

- Demanding mounting applications in EV battery
- Cell to cell mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-----------------|
| • Backing material | PET | • Total thickness | 150 µm |
| • Type of adhesive | tackified acrylic | • Colour | transparent |
| • Type of liner | glassine | • Colour of liner | brown/blue logo |

Properties/Performance Values

- | | | | |
|---|-----------|-------------------------------|--------|
| • Dielectric breakdown voltage | 14800 V | • Temperature resistance max. | 125 °C |
| • Temperature resistance | very good | • Temperature resistance min. | -40 °C |
| • Temperature resistance long term duration | 125 °C | | |

Adhesion to Values

- | | | | |
|-----------------------|----------|-------------------------|----------|
| • Aluminium (initial) | 3.8 N/cm | • Steel (initial) | 4.1 N/cm |
| • PC (initial) | 4.8 N/cm | • Steel (after 14 days) | 6.2 N/cm |

For latest information on this product please visit <http://l.tesa.com/?ip=58363>



tesa[®] 58363

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58363>