




tesa[®] 61220

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PETP	• Color	black
• Type of adhesive	specialty	• Color of liner	transparent
• Type of liner	PET	• Thickness of liner	50 µm
• Total thickness	200 µm		

Properties/Performance Values

• Elongation at break	90 %	• Humidity resistance	very good
• Tensile strength	73.3 N/cm	• Tack	medium
• Ageing resistance (UV)	very good	• Temperature resistance long term	70 °C
• Chemical Resistance	very good	• Temperature resistance short term	120 °C

Adhesion to Values

• ABS (initial)	12.8 N/cm	• PC (initial)	14.1 N/cm
• ABS (covered side, after 14 days)	14.5 N/cm	• PC (after 14 days)	24 N/cm
• Aluminium (initial)	12.6 N/cm	• PE (initial)	7 N/cm
• Aluminium (after 14 days)	15.1 N/cm	• PE (after 14 days)	8.5 N/cm
• Glass (initial)	15.5 N/cm	• Steel (initial)	16.6 N/cm
• Glass (after 14 days)	16.8 N/cm	• Steel (after 14 days)	17.5 N/cm



tesa[®] 61220

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=61220>