




tesa® 64830 Bond & Detach



Product Information

300 µm d/s White Bond&Detach Tape

Product Description

tesa® 64830 is a white stretch release tape with very good tearing resistance and high shock performance

Product Features

- Thickness: 300 µm
- High tack
- High impact resistance
- Very high bonding strength
- Very good tear resistance
- Easy removability by stretching the tape
- The tape can be removed even after a long bonding time
- Residue free removability
- IPX8

Application Fields

- Battery mounting
- Permanent mounting of valuable components in electronic devices with the option to remove the parts for repairing or recycling
- Temporary fixation of components

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------------------|----------------------|-------------|
| • Backing | stretchable specialty | • Color | white |
| • Type of adhesive | specialty | • Color of liner | transparent |
| • Type of liner | PET | • Thickness of liner | 50 µm |
| • Total thickness | 300 µm | | |

Product Assortment

- | | | | |
|--------------------|-------|--------------------|-----|
| • Available colors | white | • Available liners | PET |
|--------------------|-------|--------------------|-----|



tesa[®] 64830

Bond & Detach

Product Information

Properties/Performance Values

- | | | | |
|-------------------------------------|-----------|-------------------------------------|-----------|
| • Ageing resistance (UV) | medium | • Static shear resistance at 23°C | very good |
| • Humidity resistance | good | • Static shear resistance at 40°C | very good |
| • Removability after 14 days (23°C) | very good | • Temperature resistance long term | 60 °C |
| • Residue-free removability | yes | • Temperature resistance short term | 90 °C |

Adhesion to Values

- | | | | |
|-----------------------------|---------|-------------------------|---------|
| • Aluminium (initial) | 10 N/cm | • PE (initial) | 10 N/cm |
| • Aluminium (after 14 days) | 10 N/cm | • PE (after 14 days) | 10 N/cm |
| • Magnesium (initial) | 10 N/cm | • Steel (initial) | 12 N/cm |
| • Magnesium (after 14 days) | 10 N/cm | • Steel (after 14 days) | 12 N/cm |

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=64830>