



58451

Product Information

30µm black electrically conductive (XYZ) reactive HAF mounting tape

Product Description

tesa HAF® 58451 is a reactive heat activated film based on phenolic resin and nitrile rubber with electrically conductive properties. This black double sided tape has no backing. It is protected by a 50 µm PET liner.

At room temperature tesa HAF® 58451 is not tacky. It is activated by heat and pressure applied during the assembly process.

Special features:

- Extremely high performance, even on small bonding areas and thin design gaps
- Excellent electrical conductivity in XYZ-direction
- Superior anti-repulsion properties even at elevated temperatures
- Outstanding chemical resistance

Application Fields

tesa HAF® 58451 is especially recommended for bonding of various metal surfaces, e.g. SUS or AL.

- Grounding applications with structural bonding requirements
- Narrow and small bonding areas but still need very strong bonding strength
- High repulsion force applications such as curved or bended bonds
- Grounding applications exposed to high temperature and humidity

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------------------------------|-------------------|-------|
| • Backing | none | • Total thickness | 30 µm |
| • Type of adhesive | nitrile rubber /
phenolic resin | • Color | black |
| • Type of liner | PET | | |

Properties/Performance Values

- | | | | |
|------------------------------------|---------------------|------------------------------------|----------|
| • Bonding strength (dynamic shear) | 5 N/mm ² | • Surface resistance x-y-direction | 500 mOhm |
| • Contact resistance z-direction | 50 mOhm | | |

Additional Information

Technical recommendations: tesa HAF® 58451 is not self adhesive. It is activated by heat and pressure over a certain interval. The following values are recommendations for bond line parameters to start with.

For latest information on this product please visit <http://l.tesa.com/?ip=58451>



58451

Product Information

Additional Information

1. Pre-lamination: During pre-lamination, the tape is laminated onto one component.

Setting:

- Temperature¹ ≥ 120 °C
- Pressure² ≥ 5 bar
- Time 5 - 10 s

2. Bonding: Remove the liner from the tape after pre-lamination step. Place the pre-laminated component onto the substrate to bond with. Apply sufficient temperature while applying pressure for the bonding time to reach sufficient bonding strength.

Setting:

- Temperature¹ 120-250 °C
- Pressure² 5-30 bar
- Time 5 s – 3 min

¹ 'Pre-lamination' and 'Bonding' temperature refer to the data that is measured in the bond line. ² 'Pre-lamination' and 'Bonding' pressure refer to the force that is transformed from jig surface directly to the bonding area. Bonding strength values were obtained under standard laboratory conditions. (Material: SUS test specimen / bonding conditions: temperature = 180 °C; pressure = 30 bar; time = 30 sec). To reach maximum bonding strength surfaces should be clean and dry.

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58451>