



# **Product Information**

## 125µm double sided transparent high performance filmic tape

#### **Product Description**

tesa® 61370 is a double sided self-adhesive tape consisting of a transparent PET backing and a tackified acrylic adhesive.

#### **Product Features**

- Thickness: 125µm
- Very high bonding strength
- Superior push out resistance
- Excellent resistance to demanding environmental conditions
- High shock resistance

#### **Application Fields**

- Lens mounting in mobile phones
- Touch panel mounting

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li><li>Total thickness</li></ul>	PET film tackified acrylic glassine 125 μm	<ul><li>Color of liner</li><li>Thickness of liner</li><li>71</li></ul>	ansparent hite with tesa logo μm ) g/m <sup>2</sup>			
Properties/Performance Values						
<ul><li>Elongation at break</li><li>Tensile strength</li><li>Ageing resistance (UV)</li></ul>	50 % 20 N/cm very good	• Tack me	ood edium 0 °C			

٠	Ageing resistance (UV)	very good
•	Humidity resistance	very good
•	Static shear resistance at 23°C	good

•	remperature resistance long	100 C
	term	
•	Temperature resistance short	200 °C
	term	





# **Product Information**

### **Adhesion to Values**

•	ABS (initial)	8.7 N/cm
٠	ABS (after 14 days)	12.8 N/cm
٠	Glass (initial)	12.8 N/cm
٠	Glass (after 14 days)	15.2 N/cm
•	PC (initial)	11.2 N/cm

•	PC (after 14 days)	17.9 N/cm
٠	PMMA (initial)	13 N/cm
•	PMMA (after 14 days)	16.8 N/cm
•	Steel (initial)	13.9 N/cm
•	Steel (after 14 days)	16.7 N/cm

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

