

tesa® 4965 Original

Product Information

Double-coated tape with high shear and temperature resistance

Product Description

tesa® 4965 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

tesa® 4965 features:

- Reliable bond even to LSE substrates
- Immediate usability after assembly
- · Suitability for most demanding applications such as heavy stress, high temperatures or critical substrates

Sustainable Aspects



For more information: https://www.tesa.com/product-sustainability

Application Fields

- · Mounting of ABS plastic parts in the car industry
- Self-adhesive mounting of rubber/EPDM profiles
- · Mounting of decorative profiles and mouldings in the furniture industry
- · Mounting of battery packs, lenses and touch-screens in electronic devices

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

Type of liner

•	Backing	Post consumer recycled PET	Total thickness Color	205 μm transparent
•	Bio-based carbon content of liner (acc. DIN EN 16640)	90 %	Color of liner Thickness of liner	red 80 μm
•	Type of adhesive	biomass-balanced tackified acrylic		

MOPP



tesa® 4965 Original

Product Information

Properties/Performance Values

•	Elongation at break Tensile strength Ageing resistance (UV) Chemical Resistance Humidity resistance	50 % 20 N/cm good good very good	•	Static shear resistance at 23°C Static shear resistance at 40°C Tack Temperature resistance long term	very good very good good 100°C
•	Softener resistance	good		Temperature resistance min. Temperature resistance short term	-40 °C 200 °C

Adhesion to Values

•	ABS (initial)	10.3 N/cm	•	PET (after 14 days)	9.5 N/cm
•	ABS (after 14 days)	12 N/cm	•	PP (initial)	6.8 N/cm
•	Aluminium (initial)	9.2 N/cm	•	PP (after 14 days)	7.9 N/cm
•	Aluminium (after 14 days)	10.6 N/cm	•	PS (initial)	10.6 N/cm
•	PC (initial)	12.6 N/cm	•	PS (after 14 days)	12 N/cm
•	PC (after 14 days)	14 N/cm	•	PVC (initial)	8.7 N/cm
•	PE (initial)	5.8 N/cm	•	PVC (after 14 days)	13 N/cm
•	PE (after 14 days)	6.9 N/cm	•	Steel (initial)	11.5 N/cm
•	PET (initial)	9.2 N/cm	•	Steel (after 14 days)	11.8 N/cm

Certificates

Sustainability Certificates

tesa® 4965 Original Next Gen contains a total of 62% biocarbon content (including red MOPP liner), which is composed of 20% bio-based carbon content directly derived from biological sources and 42% bio-attributed carbon content from the use of biomass balanced adhesive components that are ISCC PLUS certified.

The double-sided mounting tape contains a 90% recycled PET backing, resulting in an average of 5% post-consumer recycled content (including red MOPP liner) in the tape. This is a third-party environmental claim validated against the UL Environmental Claim Validation Procedure 2809 for recycled content. The UL Environmental Claim Validation Program falls under UL's ISO/IEC 17025 accreditation.

Additional Information

Liner variants:

PV0 red MOPP-film (80μm; 72g/m²) PV1 brown glassine paper (71μm; 82g/m²)

PV4 white with blue tesa® logo PE-coated paper (118µm; 120g/m²)

PV7 transparent PET-film (50 μ m; 72g/m²)

PV11 white PET-film (50µm; 72g/m²)

PV36 double-liner: red MOPP-film (80μm; 72g/m²) and brown glassine paper (71μm; 82g/m²)



tesa® 4965 Original

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

