




tesa® 4974

Product Information



Double-sided tape with fabric backing

Product Description

tesa® 4974 consists of a fabric backing with a rubber adhesive system.

tesa® 4974 has very good initial adhesion.

Product Features

- tesa® 4974 has very good initial adhesion.

Application Fields

tesa® 4974 is particularly suited for mounting on rough, fibrous surfaces.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|----------------|-------------------|--------|
| • Backing | cloth | • Total thickness | 380 µm |
| • Type of adhesive | natural rubber | • Color | white |
| • Type of liner | creped paper | • Color of liner | white |

Properties/Performance Values

- | | | | |
|--------------------------|---------|-------------------------------------|--------|
| • Elongation at break | 4 % | • Static shear resistance at 23°C | low |
| • Tensile strength | 80 N/cm | • Static shear resistance at 40°C | low |
| • Ageing resistance (UV) | medium | • Tack | good |
| • Chemical Resistance | low | • Temperature resistance long term | 30 °C |
| • Humidity resistance | medium | • Temperature resistance short term | 110 °C |
| • Softener resistance | good | | |



tesa[®] 4974

Product Information

Adhesion to Values

• ABS (initial)	4.1 N/cm	• PET (after 14 days)	5 N/cm
• ABS (after 14 days)	5.6 N/cm	• PP (initial)	3.3 N/cm
• Aluminium (initial)	3.9 N/cm	• PP (after 14 days)	4.7 N/cm
• Aluminium (after 14 days)	5.3 N/cm	• PS (initial)	4.3 N/cm
• PC (initial)	4.9 N/cm	• PS (after 14 days)	5.9 N/cm
• PC (after 14 days)	5.9 N/cm	• PVC (initial)	4 N/cm
• PE (initial)	2.8 N/cm	• PVC (after 14 days)	5.1 N/cm
• PE (after 14 days)	3.6 N/cm	• Steel (initial)	5 N/cm
• PET (initial)	4.2 N/cm	• Steel (after 14 days)	6.1 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04974>