



tesa[®] 61140

Product Information

200µm double sided black differential filmic tape

Product Description

tesa[®] 61140 is a black, double sided self-adhesive tape consisting of a black PET backing coated with a reworkable adhesive on the open side and permanent strong adhesive on the covered side.

Special features:

- Thickness: 200µm
- Covered side: Very high bonding strength
- Open side: Easy reworkability and no residues on relevant substrates
- Superior handling and processing performance due to very strong PET backing
- Excellent resistance to demanding environmental conditions
- Black color

Product Features

- Thickness: 200µm
- Covered side: Very high bonding strength
- Open side: Easy reworkability and no residues on relevant substrates
- Superior handling and processing performance due to very strong PET backing
- Excellent resistance to demanding environmental conditions

Application Fields

Mounting of components in electronic devices with the option to rework the bonding during the production process.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|--------------|-----------------------------------|---------------------|
| • Backing | PET film | • Color of liner | brown |
| • Type of adhesive | pure acrylic | • Thickness of liner | 71 µm |
| • Type of liner | glassine | • Type of adhesive (covered side) | tackified acrylic |
| • Total thickness | 200 µm | • Weight of liner | 80 g/m ² |
| • Color | black | | |



tesa[®] 61140

Product Information

Properties/Performance Values

• Elongation at break	90 %	• Tack	good, medium
• Tensile strength	73.3 N/cm	• Temperature resistance long term	80 °C
• Static shear resistance at 23°C	medium, good	• Temperature resistance short term	120 °C
• Static shear resistance at 40°C	medium, good		

Adhesion to Values

• Glass (initial)	8 N/cm	• PMMA (initial)	9 N/cm
• Glass (after 14 days)	10 N/cm	• PMMA (after 14 days)	10 N/cm
• Glass (covered side, after 14 days)	19 N/cm	• PMMA (covered side, after 14 days)	20 N/cm
• Glass (covered side, initial)	18 N/cm	• PMMA (covered side, initial)	18 N/cm
• PC (initial)	10 N/cm	• Steel (initial)	8 N/cm
• PC (after 14 days)	10 N/cm	• Steel (after 14 days)	9 N/cm
• PC (covered side, after 14 days)	19 N/cm	• Steel (covered side, after 14 days)	18 N/cm
• PC (covered side, initial)	18 N/cm	• Steel (covered side, initial)	14 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=61140>