



# tesa<sup>®</sup> 62932

## Product Information



500µm double sided black/white foam tape

## Product Description

tesa<sup>®</sup> 62932 is a double-sided PE-foam tape for constructive mounting applications. It consists of a conformable PE-foam backing and a tackified acrylic adhesive.

Product benefits:

- Thin foam backing for a small design gap
- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- UV, water and ageing resistant
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorption

## Product Features

- Thin foam backing for a small design gap
- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorption

## Application Fields

- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded decorative profiles for refrigerators or freezers
- Glass and mirror panels

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                   |                   |             |
|--------------------|-------------------|-------------------|-------------|
| • Backing          | PE foam           | • Total thickness | 500 µm      |
| • Type of adhesive | tackified acrylic | • Color           | black/white |



# tesa® 62932

## Product Information

### Properties/Performance Values

• Elongation at break	270 %	• Static shear resistance at 23°C	good
• Tensile strength	8 N/cm	• Static shear resistance at 40°C	good
• Ageing resistance (UV)	good	• Tack	good
• Chemical Resistance	good	• Temperature resistance long term	80 °C
• Humidity resistance	very good	• Temperature resistance short term	80 °C
• Softener resistance	medium		

### Adhesion to Values

• ABS (initial)	14 N/cm	• PET (after 14 days)	17 N/cm
• ABS (after 14 days)	17 N/cm	• PP (initial)	1.8 N/cm
• Aluminium (initial)	13 N/cm	• PP (after 14 days)	3.3 N/cm
• Aluminium (after 14 days)	17 N/cm	• PS (initial)	10.5 N/cm
• PC (initial)	9 N/cm	• PS (after 14 days)	17 N/cm
• PC (after 14 days)	17 N/cm	• PVC (initial)	14.5 N/cm
• PE (initial)	1.7 N/cm	• PVC (after 14 days)	17 N/cm
• PE (after 14 days)	3 N/cm	• Steel (initial)	13 N/cm
• PET (initial)	12.5 N/cm	• Steel (after 14 days)	17 N/cm

### Additional Information

Liner variants:

PV0 brown glassine paper (71 µm)

PV10 red filmic liner (120 µm)

PV14 white PE-coated paper (120 µm)

PV15 blue PE (100 µm)

Peel Adhesion:

- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC



# tesa<sup>®</sup> 62932

## Product Information

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62932>