



tesa® 62708 PV0



Product Information

Double-sided PE foam tape

Product Description

tesa® 62708 is a double-sided tape consisting of a PE foam backing and a pure acrylic adhesive.

tesa® 62708 features especially:

- Excellent temperature resistance performance
- High ultimate adhesive strength for a secure bonding performance
- Conformable foam backing to compensate design tolerances or uneven surfaces
- Excellent converting properties

Product Features

- Excellent temperature resistance
- Excellent converting properties
- High ultimate adhesive strength
- Conformable foam backing to compensate for design tolerances or uneven surfaces
- Excellent cold shock performance
- The tape combines very good cohesive strength with a comparatively low density contributing positively to a low weight design.
- The PE foam backing also provides non-sticky edges resulting in excellent converting properties, e.g. for die cutting.
- Due to the high conformability, the tape ensures a good wet out and secure bonding even on uneven surfaces and compensates for design tolerances.
- The black color allows for an almost invisible bond line.

Application Fields

Permanent mounting of emblems and letters; e.g. single letters for classification of car model or engine data.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|--------------|-------------------|---------|
| • Backing | PE foam | • Total thickness | 8000 µm |
| • Type of adhesive | pure acrylic | • Color | black |
| • Type of liner | MOPP | | |



tesa[®] 62708 PV0

Product Information

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|-------------------------------------|-----------|
| • Elongation at break | 440 % | • Static shear resistance at 70°C | very good |
| • Tensile strength | 18 N/cm | • Temperature resistance long term | 100 °C |
| • Static shear resistance at 40°C | very good | • Temperature resistance short term | 120 °C |

Adhesion to Values

- | | | | |
|-----------------------|---------|--------------------------|---------|
| • ABS (initial) | 5 N/cm | • Steel (after 14 days) | 15 N/cm |
| • ABS (after 14 days) | 15 N/cm | • Steel (initial, 1 min) | 8 N/cm |
| • Steel (initial) | 4 N/cm | | |

Additional Information

Liner variants:

PV0: brown glasine paper (71µm)

PV6: red MOPP film (80µm)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62708>