



# tesa® 62530

## Product Information



Double sided PE-foam mounting tape

### Product Description

tesa® 62939 is a double-sided PE-foam tape for general mounting applications. It consists of a highly conformable closed cell PE-foam backing and a tackified acrylic adhesive.

Product benefits:

- Good adhesion on strongly structured surfaces
- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate adhesion even at low bonding pressure
- Very good cold shock absorption

### Product Features

- Good adhesion on strongly structured surfaces
- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- High immediate adhesion even at low bonding pressure
- Very good cold shock absorption

### Application Fields

- Wall skirting trims
- Dust and moisture seals
- Interior wall cladding panels

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |                   |                   |             |
|--------------------|-------------------|-------------------|-------------|
| • Backing          | PE foam           | • Total thickness | 3000 µm     |
| • Type of adhesive | tackified acrylic | • Color           | black/white |



# tesa<sup>®</sup> 62530

## Product Information

### Properties/Performance Values

• Elongation at break	160 %	• Static shear resistance at 23°C	good
• Tensile strength	13.3 N/cm	• Static shear resistance at 40°C	good
• Ageing resistance (UV)	good	• Tack	good
• Batteries required	no	• Temperature resistance long term	80 °C
• Chemical Resistance	very good	• Temperature resistance short term	80 °C
• Humidity resistance	very good	• Tensibility	140 %
• Softener resistance	medium		

### Adhesion to Values

• ABS (initial)	6 N/cm	• PET (after 14 days)	6 N/cm
• ABS (after 14 days)	6 N/cm	• PP (initial)	6 N/cm
• Aluminium (initial)	6 N/cm	• PP (after 14 days)	6 N/cm
• Aluminium (after 14 days)	6 N/cm	• PS (initial)	6 N/cm
• PC (initial)	6 N/cm	• PS (after 14 days)	6 N/cm
• PC (after 14 days)	6 N/cm	• PVC (initial)	6 N/cm
• PE (initial)	2 N/cm	• PVC (after 14 days)	6 N/cm
• PE (after 14 days)	2 N/cm	• Steel (initial)	6 N/cm
• PET (initial)	6 N/cm	• Steel (after 14 days)	6 N/cm

### Additional Information

Peel Adhesion:

- Immediate and after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

Longterm dampening properties and temperature resistance have been certified by ift institute, Germany (Report no. 105 32948/1)

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62530>