



# tesa<sup>®</sup> 60151 Adhesion Promoter Glass



## Product Information

Adhesion Promoter for Glass

## Product Description

tesa<sup>®</sup> Adhesion Promoter is used to improve the adhesion of tesa<sup>®</sup> ACX<sup>plus</sup> tapes to glass.

## Product Features

- It is especially recommended for our tesa<sup>®</sup> ACX<sup>plus</sup> product family

## Application Fields

Only for glass. Not recommended for laquered and foil-coated glass.  
Used to enhance the bonding strength and to avoid humidity on the glass.

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- Color transparent, optically clear

## Properties/Performance Values

- |               |                        |                      |                      |
|---------------|------------------------|----------------------|----------------------|
| • Consistency | liquid                 | • Spreading rate ca. | 15 m <sup>2</sup> /l |
| • Density     | 0.81 g/cm <sup>3</sup> | • Viscosity          | 2.5 mPa s            |
| • Solids      | 0.5 %                  |                      |                      |

## Additional Information

The bonding surface should be free of dust, grease, oil, moisture and other contaminants before using tesa<sup>®</sup> Adhesion Promoter 60151 for glass.

Clean the substrate with a lint free cloth and appropriate solvents, such as Ethanol or Isopropanol.

Then apply tesa<sup>®</sup> Adhesion Promoter 60151 thinly to the bonding surface, making sure that the entire surface is coated.

The Adhesion Promoter can be applied with a lint free cloth or brush, application pen or felt applicator. For best performance use a second/clean lint free cloth to remove excess of promoter.

Wait 30 seconds to 5 minutes to give the solvents time to evaporate.

Keep the prepared surface free from contaminants prior to applying tesa<sup>®</sup> ACX<sup>plus</sup> tape.

Open time for bonding are around 5 to 15 minutes.

Shelf life are 12 month when stored in the original container at room temperature.

For all further information kindly refer to the respective material safety data sheet (MSDS).

For latest information on this product please visit <http://l.tesa.com/?ip=60151>



# tesa<sup>®</sup> 60151

## Adhesion Promoter Glass

Product Information

**Additional Information**

<http://www.tesa.com/company/safety/msds>

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=60151>