



tesa[®] 62906 PV0



Product Information

Double-sided PE foam tape

Product Description

tesa[®] 62906 is a double-sided tape consisting of a PE foam backing and an acrylic adhesive.
tesa[®] 62906 features especially:

- High initial and ultimate adhesive strength for a secure bonding performance
- Conformable foam backing to compensate design tolerances or uneven surfaces
- Excellent temperature resistance performance
- Excellent converting properties

Application Fields

Permanent mounting of emblems, scriptings;
e.g. single letters for classification of car model or engine data.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|---------|-------------------|--------------------|
| • Backing | PE foam | • Total thickness | 600 µm |
| • Type of adhesive | acrylic | • Color | 23.6 mils
black |

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------------------|-------------------------------------|------------------|
| • Elongation at break | 320 % | • Static shear resistance at 70°C | good |
| • Tensile strength | 11 N/cm
6.3 lbs/in | • Temperature resistance long term | 100 °C
212 °F |
| • Static shear resistance at 40°C | good | • Temperature resistance short term | 110 °C
230 °F |

Adhesion to Values

- | | | | |
|-----------------------|------------------------|-------------------------|------------------------|
| • ABS (initial) | 6 N/cm
54.8 oz/in | • PET (after 14 days) | 19 N/cm
173.6 oz/in |
| • ABS (after 14 days) | 19 N/cm
173.6 oz/in | • Steel (initial) | 18 N/cm
164.5 oz/in |
| • PC (after 14 days) | 19 N/cm
173.6 oz/in | • Steel (after 14 days) | 19 N/cm
173.6 oz/in |

For latest information on this product please visit <http://l.tesa.com/?ip=62906>



tesa[®] 62906 PV0

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62906>