



**Product Information** 



## 100µm d/s filmic high performance tape

#### **Product Description**

tesa® 61360 is a double-sided self-adhesive tape consisting of a transparent PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 100µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- · Excellent resistance to demanding environmental conditions

### **Application Fields**

- · Lens mounting in mobile phones
- Touch panel mounting

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

# **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li><li>Total thickness</li></ul>	PET film tackified acrylic glassine 100 μm 3.9 mils	<ul> <li>Color</li> <li>Color of liner</li> <li>Thickness of liner</li> <li>Weight of liner</li> </ul>	transparent white with tesa logo 69 μm 2.7 mils 80 g/m <sup>2</sup>		
Properties/Performance Values					
<ul><li>Elongation at break</li><li>Tensile strength</li></ul>	50 % 20 N/cm 11.4 Ibs/in	<ul> <li>Static shear resistance at 40°C</li> <li>Temperature resistance long term</li> </ul>	C good 100 °C 212 °F		

term

• Temperature resistance short

200 °C

392 °F

•	Ageing	resistance	(UV)

very good Humidity resistance very good

09/04/2
of
as
2
of
~
Page

I – en-TT





# **Product Information**

#### **Adhesion to Values**

ABS (initial)	7.8 N/cm
	71.3 oz/in
<ul> <li>ABS (after 14 days)</li> </ul>	11.3 N/cm
	103.2 oz/in
<ul> <li>ABS (covered side, after 14</li> </ul>	11.2 N/cm
days)	102.3 oz/in
<ul> <li>ABS (covered side, initial)</li> </ul>	9.4 N/cm
	85.9 oz/in
<ul> <li>Glass (initial)</li> </ul>	12.5 N/cm
	114.2 oz/in
<ul> <li>Glass (after 14 days)</li> </ul>	14.5 N/cm
	132.5 oz/in
• PC (initial)	9 N/cm
	82.2 oz/in
<ul> <li>PC (after 14 days)</li> </ul>	17.7 N/cm
	161.7 oz/in

٠	PC (covered side, after 14 days)	18.3 N/cm
•	PC (covered side, initial)	167.2 oz/in 10.2 N/cm
		93.2 oz/in
٠	PMMA (initial)	12.6 N/cm
		115.1 oz/in
٠	PMMA (after 14 days)	16.7 N/cm
		152.6 oz/in
•	Steel (initial)	13.7 N/cm
		125.2 oz/in
•	Steel (after 14 days)	16.5 N/cm
		150.7 oz/in
•	Steel (covered side, after 14	17.6 N/cm
	days)	160.8 oz/in
•	Steel (covered side, initial)	14.2 N/cm
		129.7 oz/in

# Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

