



tesa[®] 75007

low VOC



Product Information

75µm reinforced tackified acrylic adhesive layer with PET scrim for mounting in automotive interiors

Product Description

tesa[®] 75007 is a conformable transparent adhesive layer of tackified acrylic reinforced with a PET scrim mesh.

Features:

- *low VOC - no critical substances detectable
- *high initial tack and peel adhesion
- *high conformable design following 3D shapes
- *provides excellent conformability and stability
- *provides excellent initial adhesion to a wide variety of interior substrates
- *suitable for the bonding to nonpolar plastics, foams, felts and fabrics
- *the scrim provides a reinforcement of flexible substrates for improving converting efficiency and handling

Product Features

- Highly conformable to follow difficult 3-D shapes
- Low VOC (acc. GB 27630) – no critical substances detectable
- Reinforcement supports converting efficiency
- Very good humidity resistance
- High initial tack and excellent repulsion resistance
- Secure mounting even to nonpolar plastics (PP) and composites (recycled materials)
- Very good initial adhesion to a wide variety of interior substrates

Application Fields

mounting of plastics as well LSE plastics

*with difficult wet-out

*permanent low load

Lamination or mounting of critical, soft, light and smooth surfaces / sheets

*immediate and secure bending around the edge



tesa[®] 75007

low VOC

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	none	• Color	transparent
• Type of adhesive	tackified acrylic	• Color of liner	brown/blue logo
• Type of liner	glassine	• Thickness of tape	75 µm
• Total thickness	75 µm 3 mils		3 mils

Product Assortment

- Available thicknesses 75 µm (tesa[®] 75007),
130 µm (tesa[®] 75013)

Properties/Performance Values

• Fogging	good	• Tack	very good
• Low VOC	very good	• Temperature resistance max.	170 °C
• Suitable for die cutting	yes		338 °F
• Suitable for rough surfaces	very good	• Temperature resistance min.	-40 °C
			-40 °F

Adhesion to Values

• ABS (initial)	9 N/cm 82.2 oz/in	• PP (initial)	5 N/cm 45.7 oz/in
• ABS (after 3 days)	10 N/cm 91.4 oz/in	• PP (after 3 days)	6 N/cm 54.8 oz/in
• PC (initial)	10.4 N/cm 95 oz/in	• PS (initial)	7.7 N/cm 70.3 oz/in
• PC (after 3 days)	11.3 N/cm 103.2 oz/in	• PS (after 3 days)	8.9 N/cm 81.3 oz/in
• PE (initial)	4.5 N/cm 41.1 oz/in	• PVC (initial)	3.9 N/cm 35.6 oz/in
• PE (after 3 days)	4.9 N/cm 44.8 oz/in	• PVC (after 3 days)	8.8 N/cm 80.4 oz/in
• PET (initial)	5.5 N/cm 50.2 oz/in	• Steel (initial)	7.3 N/cm 66.7 oz/in
• PET (after 3 days)	5.9 N/cm 53.9 oz/in	• Steel (after 3 days)	8.6 N/cm 78.6 oz/in

For latest information on this product please visit <http://l.tesa.com/?ip=75007>



tesa[®] 75007

low VOC

Product Information

Storage Conditions

Storage Conditions

23°C, 50% RH, stored in original box

Additional Information

Is designed to fulfill the low VOC (Volatile Organic Compounds) automotive requirements set forth by the Japanese Ministry of Health, Labor and Welfare (MHLW) and the Japanese Automobile Manufacturers Association (JAMA) limit of concentrations of 13 toxic chemistries. Acc. Toyota TSK0508G our assortment is conform Japanese automotive requirements

Adhesion vaules to:

PVC
PP
ABS
PC
PET
PS
PE

Are not part of the product specification

PV20 brown glassine liner / blue tesa logo
other liner version possible - on request

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=75007>