

tesa® 60233

Product Information

60µm/2.4 mils single sided matte black electrically conductive tape xy-axis

Product Description

tesa® 60233 is a matte black single sided electrically conductive self adhesive tape. It consists of a matte black PET backing which is laminated with an Aluminium foil and a conductive non-woven. The backing is coated on the non-woven side with an electrically conductive adhesive.

tesa® 60233 features especially:

- Thickness: 60μm/2.4 mils
- Excellent electrical conductivity in XY-direction for very good grounding performance
- PET film on the surface provides insulation function
- · High adhesion level even at harsh environmental conditions avoids edge lifting
- Minimized curling for easy processing and lamination
- · Matte black surface (low gloss) with anti-finger print and solvent resistant characteristic

Product Features

- Thickness: 60µm
- · Excellent electrical conductivity in XY-direction for very good grounding performance
- PET film on the surface provides insulation function
- · High adhesion level even at harsh environmental conditions avoids edge lifting
- Minimized curling for easy processing and lamination
- · Matte black surface (low gloss) with anti-finger print and solvent resistant characteristic

Application Fields

· Grounding of LCD to metal BLU chassis

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

| • | Backing | Black PET / alu foil / | • | Color | matte black |
|---|------------------|------------------------|---|--------------------|-----------------|
| | | conductive non- | • | Color of liner | white/blue logo |
| | | woven | • | Thickness of liner | 50 μm |
| • | Type of adhesive | conductive acrylic | | | 2 mils |
| • | Type of liner | PE-coated paper | | | |



tesa® 60233

Product Information

Properties/Performance Values

Release of liner easy
Static shear resistance at 23°C good
Static shear resistance at 40°C good

Surface resistance x-y-direction 0.2 mOhm
Temperature resistance short term 200 °C 392 °F

Adhesion to Values

Steel (after 14 days)
5 N/cm
45.7 oz/in

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

