



# tesa<sup>®</sup> 7160

## Product Information

60µm solid black single-sided adhesive tape

### Product Description

tesa<sup>®</sup> 7160 is a solid black, single-sided self-adhesive tape consisting of a black PET film backing and a black tackified acrylic adhesive

tesa<sup>®</sup> 7160 features esp.

- Thickness: 60µm
- Excellent light blocking performance
- Very high peel strength and shear resistance
- Very good repulsion resistance
- Handles very well in converting processes
- Excellent resistance to demanding environmental conditions
- Pinhole-free product design
- Very high electrical resistance

### Product Features

- Thickness: 60µm
- Excellent light blocking performance
- Very high peel strength and shear resistance
- Very good repulsion resistance properties
- Very good handling performance in converting processes
- Excellent resistance to demanding environmental conditions
- Pin whole free product design
- Very high electrical resistance

### Application Fields

- Fixing of cables or constructive parts in LED light sources or Flat Panel displays
- Light shielding in consumer electronics parts

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing	PET film	• Total thickness	60 µm
• Type of adhesive	acrylic	• Color of liner	2.4 mils
• Type of liner	glassine	• Thickness of liner	white
			70 µm
			2.8 mils

For latest information on this product please visit <http://l.tesa.com/?ip=07160>



# tesa<sup>®</sup> 7160

## Product Information

### Properties/Performance Values

• Elongation at break	80 %	• Static shear resistance at 40°C	very good
• Tensile strength	30 N/cm 17.1 lbs/in	• Tack	good
• Ageing resistance (UV)	very good	• Temperature resistance long term	100 °C 212 °F
• Dielectric breakdown voltage	5000 V	• Temperature resistance short term	200 °C 392 °F
• Humidity resistance	good	• Transmittance (380 - 780nm) <	0.005 %
• Softener resistance	good		

### Adhesion to Values

• ABS (initial)	5.7 N/cm 52.1 oz/in	• Glass (after 14 days)	7 N/cm 64 oz/in
• ABS (after 14 days)	6.4 N/cm 58.5 oz/in	• PC (initial)	5.9 N/cm 53.9 oz/in
• Aluminium (initial)	5.2 N/cm 47.5 oz/in	• PC (after 14 days)	7 N/cm 64 oz/in
• Aluminium (after 14 days)	6.6 N/cm 60.3 oz/in	• Steel (initial)	5.9 N/cm 53.9 oz/in
• Glass (initial)	6 N/cm 54.8 oz/in	• Steel (after 14 days)	7.3 N/cm 66.7 oz/in

### Additional Information

tesa<sup>®</sup> 7160 is certified according to UL-510

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=07160>