

# tesa® 4983

## **Product Information**

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### **Product Construction**

•	Backing	PET film	•	Total thickness	30 μm
•	Type of adhesive	tackified acrylic			1.2 mils
			•	Color	transparent

## **Properties/Performance Values**

•	Elongation at break	50 %	•	Static shear resistance at 23°C	good
•	Tensile strength	20 N/cm	•	Static shear resistance at 40°C	medium
		11.4 lbs/in	•	Tack	low
•	Ageing resistance (UV)	very good	•	Temperature resistance long	100 °C
•	Chemical Resistance	good		term	212 °F
•	Humidity resistance	very good	•	Temperature resistance short	200 °C
•	Softener resistance	good		term	392 °F

#### Adhesion to Values

<ul> <li>ABS (initial)</li> </ul>	4.5 N/cm	<ul> <li>PET (after 14 days)</li> </ul>	4.8 N/cm
	41.1 oz/in		43.9 oz/in
<ul> <li>ABS (after 14 days)</li> </ul>	5.3 N/cm	<ul> <li>PP (initial)</li> </ul>	2.3 N/cm
,	48.4 oz/in	, ,	21 oz/in
Aluminium (initial)	4.1 N/cm	<ul> <li>PP (after 14 days)</li> </ul>	3.7 N/cm
, (	37.5 oz/in	(arter 11 daye)	33.8 oz/in
<ul> <li>Aluminium (after 14 days)</li> </ul>	5.5 N/cm	PS (initial)	4 N/cm
Adminiani (arter 14 days)	50.2 oz/in	i i 3 (irritial)	36.5 oz/in
<ul> <li>PC (initial)</li> </ul>	5.2 N/cm	<ul> <li>PS (after 14 days)</li> </ul>	5.2 N/cm
	47.5 oz/in		47.5 oz/in
<ul> <li>PC (after 14 days)</li> </ul>	6 N/cm	<ul> <li>PVC (initial)</li> </ul>	3.6 N/cm
	54.8 oz/in		32.9 oz/in
• PE (initial)	2 N/cm	<ul> <li>PVC (after 14 days)</li> </ul>	6.4 N/cm
, ,	18.3 oz/in		58.5 oz/in
PE (after 14 days)	3.3 N/cm	<ul> <li>Steel (initial)</li> </ul>	5.2 N/cm
. , , , , , , , , , , , , , , , , , , ,	30.1 oz/in	, ,	47.5 oz/in
. DET (initial)	4.2 N/cm	Stool (after 14 days)	7.6 N/cm
PET (initial)		<ul> <li>Steel (after 14 days)</li> </ul>	
	38.4 oz/in		69.4 oz/in



tesa® 4983

**Product Information** 

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

