




tesa® 61390

Product Information



200µm d/s filmic high performance tape

Product Description

tesa® 61390 is a double sided self-adhesive tape consisting of a transparent PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 200µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions

Application Fields

- Lens mounting in mobile phones
- Touch panel mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PET film	• Color	transparent
• Type of adhesive	tackified acrylic	• Color of liner	white with tesa logo
• Type of liner	glassine	• Thickness of liner	69 µm
• Total thickness	200 µm	• Weight of liner	80 g/m ²
	7.9 mils		

Properties/Performance Values

• Elongation at break	50 %	• Static shear resistance at 23°C	good
• Tensile strength	20 N/cm	• Static shear resistance at 40°C	good
	11.4 lbs/in	• Temperature resistance long term	100 °C
• Ageing resistance (UV)	very good		212 °F
• Humidity resistance	very good	• Temperature resistance short term	200 °C
			392 °F



tesa[®] 61390

Product Information

Adhesion to Values

• ABS (initial)	10 N/cm 91.4 oz/in	• PC (covered side, after 14 days)	19.5 N/cm 178.2 oz/in
• ABS (after 14 days)	13.3 N/cm 121.5 oz/in	• PC (covered side, initial)	11.6 N/cm 106 oz/in
• ABS (covered side, after 14 days)	13.5 N/cm 123.3 oz/in	• PMMA (initial)	14.2 N/cm 129.7 oz/in
• ABS (covered side, initial)	10.4 N/cm 95 oz/in	• PMMA (after 14 days)	19.2 N/cm 175.4 oz/in
• Glass (initial)	14.4 N/cm 131.6 oz/in	• Steel (initial)	14.3 N/cm 130.6 oz/in
• Glass (after 14 days)	16.7 N/cm 152.6 oz/in	• Steel (after 14 days)	17 N/cm 155.3 oz/in
• PC (initial)	11.6 N/cm 106 oz/in	• Steel (covered side, after 14 days)	17 N/cm 155.3 oz/in
• PC (after 14 days)	19.8 N/cm 180.9 oz/in	• Steel (covered side, initial)	14.8 N/cm 135.2 oz/in

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=61390>