



**Product Information** 



## 150µm double sided black chemical resistant filmic tape

#### **Product Description**

tesa® 61215 is a double sided self-adhesive tape consisting of a black PET backing and a special chemical resistant adhesive.

#### **Product Features**

- Excellent chemical resistance to different polar and non polar chemical
- Excellent shock resistance
- Excellent converting performance due to PET backing
- Double PET liner
- Halogen-freeness
- Skin-compatible (ISO 10993-10:2010; ISO 10993-5:2009)

### **Application Fields**

- Cover glass mounting in wearable devices
- Mounting of parts in electronic devices, e.g. keyboard mounting and earphones

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### **Product Construction**

Backing	PET film	Color of liner - outside	transparent	
<ul> <li>Type of adhesive</li> </ul>	specialty	<ul> <li>Type of liner - inside</li> </ul>	PET	
<ul> <li>Total thickness</li> </ul>	150 μm	<ul> <li>Type of liner - outside</li> </ul>	PET	
Color	black	Weight of liner	72 g/m <sup>2</sup>	
Color of liner - inside	transparent			

#### **Properties/Performance Values**

•	Elongation at break	50 %
•	Tensile strength	20 N/cm
•	Chemical Resistance	very good
•	Humidity resistance	very good

Tack	medium
Temperature resistance long	70 °C
term	
Temperature resistance short	120 °C
term	
	Temperature resistance long term Temperature resistance short





# **Product Information**

### **Adhesion to Values**

- Aluminium (initial)
  Aluminium (after 14 days)
  Glass (initial)
  Glass (after 14 days)
  15.3 N/cm
  PC (initial)
  13.7 N/cm
- PC (after 14 days)
  PE (initial)
  PE (after 14 days)
  PE (after 14 days)
  Steel (initial)
  Steel (after 14 days)
  15.5 N/cm

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

