



# tesa<sup>®</sup> 75640

## Product Information



400µm d/s black flexible acrylic foam tape

## Product Description

tesa<sup>®</sup> 75640 is a double-sided black tape consisting of a high shock absorbing black acrylic foam.

## Product Features

- Thickness: 400µm
- Very high shock performance
- Very high thermal and cold shock resistance
- Very high bonding strength for wide temperature range
- Good anti-repulsion properties to prevent lifting
- Waterproofing
- Light blocking

## Application Fields

- Demanding touch panel, lens or screen mounting applications with high requirements for impact resistance
- Mounting of Displays and flexible OLED Displays
- Mounting of ultra slim bezel or curved designs
- Mounting of waterproof designs

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                  |                      |                      |
|--------------------|------------------|----------------------|----------------------|
| • Backing          | Acrylic          | • Color              | black                |
| • Type of adhesive | modified acrylic | • Color of liner     | transparent          |
| • Type of liner    | PET              | • Thickness of liner | 75 µm                |
| • Total thickness  | 400 µm           | • Weight of liner    | 105 g/m <sup>2</sup> |

## Properties/Performance Values

- |                                   |           |                                     |        |
|-----------------------------------|-----------|-------------------------------------|--------|
| • Ageing resistance (UV)          | very good | • Temperature resistance long term  | 90 °C  |
| • Static shear resistance at 40°C | very good | • Temperature resistance short term | 180 °C |



# tesa<sup>®</sup> 75640

## Product Information

### Adhesion to Values

• Aluminium (initial)	10 N/cm	• PC (initial)	15 N/cm
• Aluminium (after 3 days)	17 N/cm	• PC (after 3 days)	38 N/cm
• Glass (initial)	18 N/cm	• Steel (initial)	17.5 N/cm
• Glass (after 3 days)	19.5 N/cm	• Steel (after 3 days)	21 N/cm

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=75640>