



# tesa<sup>®</sup> 68582

## Product Information

50µm double sided transparent differential filmic tape

### Product Description

tesa<sup>®</sup> 68582 is a transparent, double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

The coating weight of the open side is higher than the coating weight of the covered side.

### Product Features

- Thickness: 50µm
- High adhesion level on the open side, low adhesion level on the covered side
- Excellent resistance to demanding environmental conditions
- Very good handling performance in converting processes

### Application Fields

- Mounting of two different sub-strates, where one is easy to adhere and the other one is difficult to adhere

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing	PET film	• Color	transparent
• Type of adhesive	tackified acrylic	• Color of liner	white/blue logo
• Type of liner	PE-coated paper	• Thickness of liner	122 µm
• Total thickness	50 µm	• Weight of liner	120 g/m <sup>2</sup>

### Properties/Performance Values

• Elongation at break	50 %	• Static shear resistance at 23°C	good
• Tensile strength	20 N/cm	• Static shear resistance at 40°C	medium
• Ageing resistance (UV)	very good	• Tack	medium
• Chemical Resistance	very good	• Temperature resistance long term	100 °C
• Humidity resistance	very good	• Temperature resistance short term	200 °C



# tesa<sup>®</sup> 68582

## Product Information

### Adhesion to Values

• ABS (initial)	6.5 N/cm	• PE (covered side, after 14 days)	2.6 N/cm
• ABS (after 14 days)	7.9 N/cm	• PE (covered side, initial)	1.6 N/cm
• ABS (covered side, after 14 days)	6.6 N/cm	• PET (initial)	6.5 N/cm
• ABS (covered side, initial)	4.2 N/cm	• PET (after 14 days)	7 N/cm
• PC (initial)	8.2 N/cm	• PET (covered side, after 14 days)	5.6 N/cm
• PC (after 14 days)	9.7 N/cm	• PET (covered side, initial)	4.4 N/cm
• PC (covered side, after 14 days)	7.2 N/cm	• Steel (initial)	8 N/cm
• PC (covered side, initial)	5.4 N/cm	• Steel (after 14 days)	9.2 N/cm
• PE (initial)	3.6 N/cm	• Steel (covered side, after 14 days)	7.5 N/cm
• PE (after 14 days)	4.7 N/cm	• Steel (covered side, initial)	5 N/cm

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=68582>