


7805 Black Line

제품 정보

아크릴 폼 테이프

제품 설명



Being viscoelastic, tesa® ACX^{plus} 7805 Black Line optimally absorbs and dissipates dynamic and static loads. This exceptional capability enables tesa® ACX^{plus} 7805 Black Line to compensate for extreme physical stress caused by different thermal elongation of bonded parts in changing temperature conditions.

Also available in 0.8 mm, 1.1 mm, 1.2 mm, and 1.5 mm formats.

Main features:

- * Deep black color for enhanced appearance and design flexibility
- * Excellent cold shock performance
- * High humidity and UV resistance
- * Closed cell acrylic foam core
- * Viscoelastic acrylic foam core to compensate for different thermal elongation of bonded parts

특성

- · Deep black color for enhanced appearance and design flexibility
- · Excellent cold shock performance
- · High humidity and UV resistance
- · Superior push out resistance also at high temperatures
- PFAS / PFOS free Product
- · Closed cell acrylic foam core





7805 Black Line

제품 정보

특성

· Viscoelastic acrylic foam core to compensate for different thermal elongation of bonded parts

Applications

tesa® ACX^{plus} 7805 Black Line is suitable for a wide range of exterior attachment part mounting applications.

Example applications are:

- * Emblems
- * Window laces
- * Antennas
- * Pillar appliques
- * Decorative trims

To ensure the highest performance possible, our aim is to fully understand your application (including the substrates involved) in order to provide the right product recommendation.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

제품 구조

•	기재 소재	아크릴 폼	•	총두께	500 µm
•	점착제 종류	변성 아크릴	•	컬러	deep black

• 이형지 종류 PE/PP protection film

속성 / 성능 값

•	연신률	1400 %	• 노후성 (UV)	very good
•	내습성	very good		

관련제품 최신자료는 다음의 경로를 클릭하세요 http://l.tesa.com/?ip=07805



7805 Black Line

제품 정보

점착력(수치)

• ABS점착력 (3일 경과)

18 N/cm

• Steel점착력 (3일 경과)

21 N/cm

추가정보

PV 25 = White siliconised PE-coated paper liner

PV 29 = Blue heat sealable and adhesive tabable film liner

Adhesion data are based on PV25 liner.

공지사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타문의사항이 있으시면 저희 직원에게 문의 바랍니다

