


8742

제품 정보



50µm Low Temperature Thermoplastic Structural Bonding Film

제품 설명

테사 tesa® Low Temperature Thermoplast (LTT) 8742 is a non-reactive structural bonding film activated at moderate temperatures. This translucent film has no backing. It is protected by a dark-grey PE liner. tesa® LTT 8742 is free of halogen and compliant with current RoHS directive. At room temperature tesa® LTT 8742 is not tacky. It is activated by moderate heat and pressure applied during the assembly process.

Main features

- High peel adhesion on wide variety of fabrics
- Low pre-lamination temperature starting from 60 °C
- No yellowing
- Good re-workability from smooth substrates

Applications

tesa® LTT 8742 is especially recommended for bonding of fabrics to various substrates.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

제품 구조

• 기재 소재	없음	• 총두께	50 µm
• 점착제 종류	polyurethane	• 컬러	반투명
• 이형지 종류	PE		

추가정보

Adhesion properties:

Peel adhesion to polyester fabric: 11 N/cm

Technical recommendations:

tesa® LTT 8742 is not self-adhesive. It is activated by heat and pressure over a certain interval. The following values are recommendations for bond line parameters to start with.

1) Pre-lamination

During pre-lamination, laminate the film onto the first component.

관련제품 최신자료는 다음의 경로를 클릭하세요 <http://l.tesa.com/?ip=08742>



8742

제품 정보

추가정보

Setting:

- Temperature¹ 60 – 90 °C
- Pressure² 1 – 5 bar
- Time 5 – 20 s

2) Bonding

Remove the liner from the film after the pre-lamination step. Position the second component. Apply temperature and pressure for the bonding time to reach sufficient bonding strength.

Setting:

- Temperature¹ 80 – 120 °C
- Pressure² 1 – 5 bar
- Time 10 – 480 s

Temperature, pressure and time will depend upon the type and thickness of the substrates. Generally, thicker substrates or lower bonding temperatures will require longer bonding times.

Short cycle times can be achieved at 110 °C bond line temperature. For activation at lower temperatures, increase the heat-press time or combine a short heat-press step with oven curing.

Peel adhesion values were obtained under standard laboratory conditions (reinforcement backing 23 µm PET; bonding conditions: temperature = 90 °C; pressure = 5 bar; time = 120 sec).

To reach maximum bonding strength, surfaces should be clean and dry. Allow at least 1-2 hours dwell-time after bonding before performance testing. Final bonding strength will be reached after 24 hours.

¹ 'Pre-lamination' and 'Bonding' temperature refer to the data that is measured in the bond line. ² 'Pre-lamination' and 'Bonding' pressure refer to the force that is transferred from jig surface directly to the bonding area.



8742

제품 정보

공지사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의사항이 있으시면 저희 직원에게 문의 바랍니다



관련제품 최신자료는 다음의 경로를 클릭하세요 <http://l.tesa.com/?ip=08742>