



tesa® 60150 Adhesion Promoter Universal

Product Information



Overflatebehandling til forbedring av vedheftning på forskjellige materialer

Produktbeskrivelse

tesa® 60150 Adhesion Promoter Universal kan brukes til forbedring av vedheftningen av tesas trykkfølsomme tape-produkter til forskjellige materialer, herunder zink, stål samt PP/EPDM. Produktet anbefales spesielt til bruk sammen med vår serie av ACX^{plus}-produkter. tesa® 60150 Adhesion Promoter er UV-sporbar, noe som muliggjør enkel kvalitetskontroll under påføringsprosessen. Når materialet har blitt riktig forbehandlet med tesa® Adhesion Promoter 60150, bør vedheftningen oppstå i løpet av 15 minutter. Tester har vist at vår klebe-fremmer krever betydelig høyere klebekraft.

Funksjoner

- It is especially recommended for our tesa® ACX^{plus} product family
- The UV-traceability of our tesa® 60150 Adhesion Promoter allows easy quality control during the application process

Applikasjon

- tesa® 60150 er en væske som brukes til å forbedre og fremme vedheftningen av tesa®-tape på en rekke forskjellige materialer.
- Adhesjonsfremmeren anbefales til forskjellige materialer som f.eks. PVC, PP/EPDM, ABS, zink, stål eller aluminium

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Produktinnhold

- Farge Lysegul

Egenskaper / ytelsesverdier

- | | | | |
|-----------------|------------------------|--------------|----------|
| • Dekkevne | 15 m ² /l | • Konsistens | Flytende |
| • Density | 0.81 g/cm ³ | • Viskositet | 15 mPa s |
| • Faste stoffer | 7 % | | |

Additional Information

Before using our adhesion promoter, the bonding surface should be free of dust, grease, oil, moisture, and other contaminants. Therefore, we highly recommend cleaning the substrate with a lint-free cloth using solvents, such as ethanol or isopropanol alcohol or our tesa® 60040 Industry Cleaner.

Once the surface has been cleaned, you can go ahead and apply our tesa® 60150 Adhesion Promoter. We recommend applying our adhesion promoters with a melamin sponge or lint-free cloth. The entire surface should be coated thinly with adhesion promoter in order to reach the highest bonding performance. It is important to wait at least 30 seconds and up

For latest information on this product please visit <http://l.tesa.com/?ip=60150>



tesa[®] 60150

Adhesion Promoter Universal

Product Information

Additional Information

to 5 minutes (depending on ambient temperature and humidity) in order to give solvents time to evaporate. Please make sure to keep the prepared surface free of contaminants prior to applying the tape.

Once the substrate has been properly pre-treated with tesa[®] 60150 Adhesion Promoter, the bond should be established within several hours. Please note that due to the multitude of available substrate formulations in the marketplace, it is recommended to test our tesa[®] Adhesion Promoter prior to usage.

- The shelf life of this product amounts to at least 12 months when stored at room temperature in its sealed original container.
- For further information and advice on safe handling please refer to our safety data sheet (SDS), which is available upon request.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=60150>